


MANIFATTURA TUBI GOMMA s.p.a.

 Grisignano di Zocco, 36040 (VI) ITALY
 T. +39 0444.614755 | info@mtgspa.com
 www.mtgspa.com


APPLICATION

- Multipurpose suction and delivery hose for conveying a wide range of aggressive chemicals.
- Engineered to ensure dissipation of electrostatic charges not only on the surface, but also through the hose wall (Electrical resistance: $R < 10^9 \Omega$).

CONSTRUCTION

TUBE

- UPE (Ultra High Molecular Weight Polyethylene), antistatic ($R < 10^6 \Omega$), black and white, smooth.
- Compliance: FDA Standards, Regulation EU n. 10/2011.

REINFORCEMENT

- High strength plies of synthetic cord.
- Embedded steel helix wires.
- Copper wires on request.

COVER

- EPDM rubber, black, antistatic ($R < 10^6 \Omega$), resistant to abrasion, ozone and weather, wide corrugated, cloth finish.

STANDARDS

- Execution in accordance with EN 12115:2011.

TEMPERATURE RANGE

- In accordance with EN 12115:2011.
- Resistant to steam up to $+130^\circ\text{C}$ for max. 30 minutes.

SAFETY FACTOR

- ≥ 4 times working pressure.

ELECTRICAL PROPERTIES

- Electrical resistance through the hose wall: $R < 10^9 \Omega$.
- Identification symbol:
 - Ω/T for version without copper wires;
 - M/T for version with copper wires.

NOTE

- The wide corrugation of the outer surface allows an easy and safe installation of the fittings (no cuffs needed).

MARKING

- Embossed tape according to EN 12115:2011, lengthwise.



TECHNICAL SPECIFICATIONS

SIZE TOLERANCES: Inner diameter: EN 12115 - Outer diameter: EN 12115 - Length: ISO 1307

Inner Diameter mm	Outer diameter mm	Wall thickness mm	Working pressure BAR	Burst pressure BAR	Vacuum BAR	Min. bending radius mm	Approx. weight kg/m	Max. length m
19	31	6.0	10	40	-0.90	125	0.65	40
25	37	6.0	10	40	-0.90	150	0.80	40
32	44	6.0	10	40	-0.90	175	0.95	40
38	51	6.5	10	40	-0.90	225	1.20	40
50	66	8.0	10	40	-0.90	275	1.90	40
63.5	79.5	8.0	10	40	-0.90	300	2.60	40
75	91	8.0	10	40	-0.80	350	3.00	40
100	116	8.0	10	40	-0.80	450	4.10	40

 Chemical resistance acc. to MTG Chemical Resistance Chart. Above technical data are based on application at room temperature ($+20^\circ\text{C}$). Other sizes are available on request.